



**University of  
Zurich**<sup>UZH</sup>

**Zurich Open Repository and  
Archive**

University of Zurich  
University Library  
Strickhofstrasse 39  
CH-8057 Zurich  
[www.zora.uzh.ch](http://www.zora.uzh.ch)

---

Year: 2013

---

## Some unique superconductive properties of cuprates

Müller, K A

DOI: <https://doi.org/10.1007/s10948-012-1954-x>

Posted at the Zurich Open Repository and Archive, University of Zurich

ZORA URL: <https://doi.org/10.5167/uzh-156199>

Journal Article

Published Version

Originally published at:

Müller, K A (2013). Some unique superconductive properties of cuprates. *Journal of Superconductivity and Novel Magnetism*, 26(4):743.

DOI: <https://doi.org/10.1007/s10948-012-1954-x>

# Some Unique Superconductive Properties of Cuprates

K.A. Müller

Received: 27 November 2012 / Accepted: 1 December 2012 / Published online: 30 December 2012  
© Springer Science+Business Media New York 2012

Copper oxides are the only materials that show transition temperatures,  $T_c$ , above the boiling point of liquid nitrogen, with a maximum  $T_c^m$  of 162 K under pressure. Their structure is layered, with one to several  $\text{CuO}_2$  planes, and upon hole doping, their transition temperature follows a dome-shaped curve with a maximum at  $T_c^m$ . In the underdoped regime, i.e., below  $T_c^m$ , a pseudogap  $T^*$  is found, with  $T^*$  always being larger than  $T_c$ , a property unique to the copper oxides.<sup>1</sup> In the superconducting state, Cooper pairs (two holes with antiparallel spins) are formed that exhibit coherence lengths on the order of a lattice distance in the  $\text{CuO}_2$  plane and one order of magnitude less perpendicular to it. Their macroscopic wave function is parallel to the  $\text{CuO}_2$  plane near 100 %  $d$  at their surface, but only 75 %  $d$  and 25 %  $s$  in the bulk, and near 100 %  $s$  perpendicular to the plane in YBCO. There are two gaps with the same  $T_c$  [2]. As a function of doping, the oxygen isotope effect is novel and can be quantitatively accounted for by a two-band vibronic

theory [3] near  $T_c^m$ , and underdoped below it till  $T_c = 0$  by a formula valid for (bi)polarons [4]. These cuprates are intrinsically heterogeneous in a dynamic way. In terms of quasiparticles, Jahn Teller bipolarons are present at low doping, and aggregate upon cooling [1], so that probably ramified clusters and/or stripes are formed, leading to a more Fermi-liquid-type behavior at large carrier concentrations above  $T_c^m$ .

## References

1. Müller, K.A.: J. Phys. Condens. Matter **19**, 251002 (2007)
2. Khasanov, R., Shengelaya, A., et al.: Phys. Rev. Lett. **98**, 0570007 (2007)
3. Keller, H., Bussmann-Holder, A., Müller, K.A.: Mater. Today **11**, 38 (2008)
4. Weyeneth, S., Müller, K.A.: J. Supercond. Nov. Magn. **24**, 1235 (2011)

<sup>1</sup>For an overview see [1].